

PROCEDURE RECOMMENDATION

1. RETENTION BEADS II ADHESIVE should be stored away from direct sunlight. In a long period of exposure to sunlight, the adhesive may turn into a gel.
2. When using RETENTION BEADS II SSS, apply the thinnest layer possible of wax surface wetting agent. Otherwise, it may roughen the surface of metal castings.
3. When using RETENTION BEADS II SSS and a centrifugal casting machine with changeable revolutions, set the device for more revolutions than usual to obtain high casting pressure in the first stage of movement.

Last revised: 08/2015



MANUFACTURED by
GC DENTAL PRODUCTS CORP.
2-285 Toriimatsu-cho, Kasugai, Aichi 486-0844, Japan

DISTRIBUTED by
GC CORPORATION
76-1 Hasunuma-cho, Itabashi-ku, Tokyo 174-8585, Japan

GC EUROPE N.V.
Research-Park, Interleuvenlaan 33, B-3001 Leuven, Belgium

PRINTED IN JAPAN

399317011
151056AH

RETENTION BEADS II RETENTION BEADS II ADHESIVE

Prior to use, carefully read these instructions for use.

For use only by a dental professional in the recommended indications.

Size	L	SS	SSS
Color	White	Orange	Yellow
Average particle size (µm)	600	200	100

DIRECTIONS FOR USE

1. Using the brush on the cap, apply a thin layer of RETENTION BEADS II ADHESIVE to the retention area of the wax pattern.

Note:

- a) When using RETENTION BEADS II L, apply two coats of RETENTION BEADS II ADHESIVE to provide a thick adhesion layer for the beads.
- b) To apply a thin layer of the adhesive, cut short the tip of the brush with scissors.



2. Dry thoroughly the adhesive coated surface and sprinkle RETENTION BEADS II to the entire retention area, taking care not to overlap the beads.

GC METALPRIMER II is recommended to provide a firm bond between hard resin and metal framework.

NOTE

1. Store away from high temperature and humidity. RETENTION BEADS II may stick together in humid conditions. In such a case, lightly shake the container before use.
2. RETENTION BEADS II ADHESIVE is very volatile. After use, immediately replace the cap tightly.
3. When using a centrifugal casting machine, use thick sprues with RETENTION BEADS II SSS. It is difficult to cast fused metal into the die with very small-size retainers.
4. RETENTION BEADS II ADHESIVE may discolor under many hours' exposure to direct sunlight. This will not affect its adhesive strength.
5. Highly flammable liquid and vapour. Causes serious eye irritation. May cause drowsiness or dizziness. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
Avoid breathing vapours. IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water/shower. IF IN EYES: Rinse

cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Store locked up. Dispose of contents/container in accordance with local/regional/national/international regulations.

Some products referenced in the present IFU may be classified as hazardous according to GHS. Always familiarize yourself with the safety data sheets available at:
<http://www.gceurope.com/download>

They can also be obtained from your supplier.

PACKAGES

1. RETENTION BEADS II SET
(Each size : L, SS, SSS)
RETENTION BEADS II 15 g (1),
RETENTION BEADS II ADHESIVE 10mL (1)
2. Bottle of RETENTION BEADS II 15g (1)
(Each size : L, SS, SSS)
3. Bottle of RETENTION BEADS II ADHESIVE 10mL (1)